



Standard Specification for Steel Castings, Carbon, Suitable for Fusion Welding, for High-Temperature Service¹

This standard is issued under the fixed designation A216/A216M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

^{ε1} NOTE—Table 1 and Supplementary Requirements section were editorially corrected in May 2015.

1. Scope*

1.1 This specification² covers carbon steel castings for valves, flanges, fittings, or other pressure-containing parts for high-temperature service and of quality suitable for assembly with other castings or wrought-steel parts by fusion welding.

1.2 Three grades, WCA, WCB, and WCC, are covered in this specification. Selection will depend upon design and service conditions, mechanical properties, and the high temperature characteristics.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

2. Referenced Documents

2.1 ASTM Standards:³

A488/A488M Practice for Steel Castings, Welding, Qualifications of Procedures and Personnel

A703/A703M Specification for Steel Castings, General Requirements, for Pressure-Containing Parts

A985/A985M Specification for Steel Investment Castings General Requirements, for Pressure-Containing Parts

2.2 *Manufacturers' Standardization Society of the Valve and Fittings Industry Standard:*⁴

SP 55 Steel Castings for Valve, Flanges, and Fittings, and Other Components (Visual Method)

3. General Conditions for Delivery

3.1 Except for investment castings, castings furnished to this specification shall conform to the requirements of Specification A703/A703M, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification A703/A703M constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification A703/A703M, this specification shall prevail.

3.2 Steel investment castings furnished to this specification shall conform to the requirements of Specification A985/A985M, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification A985/A985M constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification A985/A985M, Specification A985/A985M shall prevail.

4. Ordering Information

4.1 The inquiry and order should include or indicate the following:

4.1.1 A description of the casting by pattern number or drawing (dimensional tolerances shall be included on the casting drawing),

4.1.2 Grade of steel,

4.1.3 Options in the specification,

⁴ Available from Manufacturers Standardization Society of the Valve and Fittings Industry (MSS), 127 Park St., NE, Vienna, VA 22180-4602, <http://www.mss-hq.com>.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved May 1, 2014. Published May 2014. Originally approved in 1939. Last previous edition approved in 2012 as A216/A216M – 12. DOI: 10.1520/A0216_A0216M-14E01.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-216/SA-216M in Section II of that code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

4.1.4 Whether the castings are to be produced using the investment casting process, and

4.1.5 The supplementary requirements desired including the standards of acceptance.

5. Heat Treatment

5.1 All castings shall receive a heat treatment proper to their design and chemical composition.

5.2 Castings shall be furnished in the annealed, or normalized, or normalized and tempered condition unless Supplementary Requirement S15 is specified.

5.3 Heat treatment shall be performed after castings have been allowed to cool below the transformation range.

6. Temperature Control

6.1 Furnace temperatures for heat treating shall be effectively controlled by pyrometer.

7. Chemical Composition

7.1 The steel shall be in accordance with the requirements as to chemical composition prescribed in [Table 1](#).

8. Tensile Requirements

8.1 Steel used for the castings shall be in accordance with the requirements as to tensile properties prescribed in [Table 2](#).

TABLE 1 Chemical Requirements

NOTE 1—All values are maximums.

Element	Composition, %		
	Grade WCA UNS J02502	Grade WCB UNS J03002	Grade WCC UNS J02503
Carbon	0.25 ^A	0.30 ^B	0.25 ^C
Manganese	0.70 ^A	1.00 ^B	1.20 ^C
Phosphorus	0.035	0.035	0.035
Sulfur	0.035 ^D	0.035 ^D	0.035 ^D
Silicon	0.60	0.60	0.60
Specified residual elements:			
Copper	0.30	0.30	0.30
Nickel	0.50	0.50	0.50
Chromium	0.50	0.50	0.50
Molybdenum, max	0.20	0.20	0.20
Vanadium	0.03	0.03	0.03
Total of these specified residual elements ^E †	1.00	1.00	1.00

† Editorially corrected.

^A For each reduction of 0.01 % below the specified maximum carbon content, an increase of 0.04 % manganese above the specified maximum will be permitted up to a maximum of 1.10 %.

^B For each reduction of 0.01 % below the specified maximum carbon content, an increase of 0.04 % Mn above the specified maximum will be permitted up to a maximum of 1.28 %.

^C For each reduction of 0.01 % below the specified maximum carbon content, an increase of 0.04 % manganese above the specified maximum will be permitted to a maximum of 1.40 %.

^D For lower maximum sulfur content, see Supplementary Requirement S52.

^E Not applicable when Supplementary Requirement S11 is specified.

TABLE 2 Tensile Requirements

	Grade WCA	Grade WCB	Grade WCC
Tensile strength, ksi [MPa]	60 to 85 [415 to 585]	70 to 95 [485 to 655]	70 to 95 [485 to 655]
Yield strength, ^A min, ksi [MPa]	30 [205]	36 [250]	40 [275]
Elongation in 2 in. [50 mm], min, % ^B	24	22	22
Reduction of area, min, %	35	35	35

^A Determine by either 0.2 % offset method or 0.5 % extension-under-load method.

^B When ICI test bars are used in tensile testing as provided for in Specification [A703/A703M](#), the gage length to reduced section diameter ratio shall be 4 to 1.

9. Quality

9.1 The surface of the casting shall be examined visually and shall be free of adhering sand, scale, cracks, and hot tears. Other surface discontinuities shall meet the visual acceptance standards specified in the order. Visual Method SP-55 or other visual standards may be used to define acceptable surface discontinuities and finish. Unacceptable visual surface discontinuities shall be removed and their removal verified by visual examination of the resultant cavities.

9.2 When additional inspection is desired, Supplementary Requirements S4, S5, and S10 may be ordered.

9.3 The castings shall not be peened, plugged, or impregnated to stop leaks.

10. Repair by Welding

10.1 Repairs shall be made using procedures and welders qualified under Practice [A488/A488M](#).

10.2 Weld repairs shall be inspected to the same quality standards that are used to inspect the castings. When castings are produced with Supplementary Requirement S4 specified, weld repairs shall be inspected by magnetic particle examination to the same standards that are used to inspect the castings. When castings are produced with Supplementary Requirement S5 specified, weld repairs on castings that have leaked on hydrostatic test, or on castings in which the depth of any cavity prepared for repair welding exceeds 20 % of the wall thickness or 1 in. [25 mm], whichever is smaller, or on castings in which any cavity prepared for welding is greater than approximately 10 in.² [65 cm²], shall be radiographed to the same standards that are used to inspect the castings.

10.3 Castings containing any repair weld that exceeds 20 % of the wall thickness or 1 in. [25 mm], whichever is smaller, or that exceeds approximately 10 in.² [65 cm²] in area, or that was made to correct hydrostatic test defects, shall be stress relieved or heat treated after welding. This mandatory stress relief or heat treatment shall be in accordance with the procedure qualification used.

11. Keywords

11.1 carbon steel; high temperature; pressure-containing parts; steel castings

SUPPLEMENTARY REQUIREMENTS

The following supplementary requirements shall not apply unless specified in the purchase order. Lists of standardized supplementary requirements for use at the option of the purchaser are included in Specifications **A703/A703M** and **A985/A985M**. Those which are ordinarily considered suitable for use with this specification are given below. Others enumerated in Specifications **A703/A703M** and **A985/A985M** may be used with this specification upon agreement between the manufacturer and purchaser.

S1. Unspecified Elements
S2. Destruction Tests
S3. Bend Test
S4. Magnetic Particle Inspection
S5. Radiographic Inspection
S10. Examination of Weld Preparation
S11. Carbon Equivalent

S11.1 When specified on the order, the maximum carbon equivalent shall be:

Grade	Carbon Equivalent, max
WCA	0.50
WCB	0.50
WCC	0.55

S11.2 Carbon equivalent (*CE*) shall be determined as follows:

$$CE = C + \frac{Mn}{6} + \frac{Cr+Mo+V}{5} + \frac{Ni+Cu}{15}$$

S15. Quench and Temper Heat-Treatment
S16. Requirements for Carbon Steel Castings for Hydrofluoric Acid Alkylation Service

S16.1 Castings shall be provided in the normalized or normalized and tempered heat-treated condition.

S16.2 The maximum carbon equivalent shall be as follows:

Maximum specified section thickness less than or equal to 1 in. [25 mm] *CE* maximum 0.43

Maximum specified section thickness greater than 1 in. [25 mm] 0.45

S16.3 Determine the carbon equivalent (*CE*) as follows:

$$CE = C + \frac{Mn}{6} + \frac{(Cr+Mo+V)}{5} + \frac{(Ni+Cu)}{15}$$

S16.4 Vanadium and niobium maximum content based upon heat analysis shall be:

NOTE 1—Niobium = columbium

Maximum vanadium	0.02 wt %
Maximum niobium	0.02 wt %
Maximum vanadium plus niobium	0.03 wt %

S16.5 The sum of the nickel and copper contents, based upon heat analysis, shall not exceed 0.15 wt %.

S16.6 The minimum carbon content shall be 0.18 wt %. The maximum carbon content shall be as required for the appropriate grade.

S16.7 Welding consumables for repair welds shall be of the low-hydrogen type. E60XX electrodes shall not be used and the resulting weld chemistry shall meet the same chemistry requirements as the base metal.

S16.8 In addition to the requirements for product marking in the specification, an “HF-N” stamp or marking shall be provided on each casting to identify that the casting complies with this supplementary requirement.

S52. Lower Sulfur Maximum

S52.1 When specified in the order the maximum sulfur content of Grade WCA, or Grade WCB, or Grade WCC shall not exceed 0.030.

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A216/A216M–12) that may impact the use of this standard. (Approved May 1, 2014.)

(1) Revised Table 1 to provide for a Supplementary Requirement for reduced sulfur of grades WCA, WCB, and WCC.

(2) Added Supplementary Requirement S52.

Committee A01 has identified the location of selected changes to this standard since the last issue (A216/A216M–08) that may impact the use of this standard. (Approved Nov. 1, 2012.)

(1) Revised **Table 1** to reduce sulfur and phosphorous maximums of grades WCA, WCB, and WCC.

(2) Deleted S10.1.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>